



ElvaJet® Opal SC

**Sublimation ink for
industrial printers**



working for you.

Product Profile:

ElvaJet Opal SC is a series of water-based sublimation inks designed to give maximum color, print and application performance when fixed onto polyester substrates via a transfer sublimation process.

The ElvaJet Opal SC series is suitable for most printers using Kyocera piezo printheads (e.g. systems from MS Dover, EFI Reggiani, Atexco - the suitability of the inks for individual machines and models needs however to be validated by the user)

Typical characteristics and features include:

- Superior color and release from transfer papers
- Enhanced color uniformity
- Excellent image sharpness
- Certified for Eco-Passport by OEKO-TEX

Ink Installation: Unless ElvaJet Opal SC is the first ink installed into the system, it is recommended to clean the ink line thoroughly using a recommended flush.

Printing: For optimal printing, the relative humidity rate must be kept at 50% or higher and the atmospheric temperature set to 20-25°C (70°F). If the inks dry in the nozzles, the normal cleaning procedure built into the printer should be applied. It is recommended to use Universal Flush WB first.





Fixation: To obtain a good color transfer and fixing, the printed substrate should be transferred at 210°C (410°F) for 30s (40-45s for fluo colors)

Fastness:

Substrate: 170 g/m², 100 % Polyester, Printing resolution: 600 dpi, Transfer conditions: 210°C (410°F) for 30 seconds (40s for fluo colors)

Product	Light	Water (severe)	Washing (60°C)	Persp. (acid)	Persp. (alkali)	Rubbing (dry)	Rubbing (wet)
ElvaJet®	ISO 105 /B02 100% / 10%	ISO 105 /E01 ch./st.	ISO 105 /C03 ch./st.	ISO 105 /E04 ch./st.	ISO 105 /E04 ch./st.	ISO 105 /X12	ISO 105 /X12
Opal SC Yellow	6+ / 6	4-5 / 4-5	4-5 / 4-5	4-5 / 4-5	4-5 / 4-5	4-5	4-5
Opal SC Vivid Yellow	6+ / 6	4-5 / 4-5	4-5 / 4-5	4-5 / 4-5	4-5 / 4-5	4-5	4-5
Opal SC Magenta	6 / 6	4-5 / 4-5	4-5 / 4-5	4-5 / 4-5	4-5 / 4-5	4-5	4-5
Opal SC Black	6 / 5	4-5 / 4-5	4-5 / 4-5	4-5 / 4-5	4-5 / 4-5	4	4-5
Opal SC Cyan	6 / 6	4-5 / 4-5	4-5 / 4-5	4-5 / 4-5	4 / 4-5	4	4-5
Opal SC Fluo Yellow	4	4-5 / 4	4-5 / 4-5	4 / 4-5	4-5 / 5	4-5	4-5
Opal SC Fluo Red	5	4-5 / 4-5	4-5 / 4-5	4-5 / 4-5	4-5 / 4-5	4-5	4-5
Opal SC Fluo Cyan	7 / 7	5 / 5	5 / 5	5 / 5	5 / 5	4	4-5

Available Inks:

	Cyan		Fluo Cyan
	Magenta		Fluo Red
	Yellow		Fluo Yellow
	Black		Universal Flush WB
	Vivid Yellow		Parking Flush WB

ElvaJet Opal SC inks are available in a standard pack size of 5kg

Substrates: ElvaJet Opal SC is compatible with a wide range of coated and uncoated transfer papers from 22gsm.

Storage Considerations: Inks should be stored in a controlled environment at a temperature between 10-30°C. If stored under these recommended conditions, the inks have a shelf life of 12 (twelve) months. **ElvaJet Opal SC Red Fluo must be stored below 30°C to ensure stability and shelf life.**

Safety, Health and Environment: ElvaJet Opal SC inks should be used in accordance with normal standards of industrial hygiene and good manufacturing practice. Please refer to the Safety Data Sheet for specific information.

Although the information presented here is believed to be reliable, Sun Chemical Corporation makes no representation or guarantee to its accuracy, completeness or reliability of the information. All recommendations and suggestions are made without guarantee, since the conditions of use are beyond our control. There is no implied warranty of merchantability or fitness for purpose of the product or products described herein. In no event shall Sun Chemical Corporation be liable for damages of any nature arising out of the use or reliance upon the information. Sun Chemical Corporation expressly disclaims that the use of any material referenced herein, either alone or in combination with other materials, shall be free of rightful claim of any third party including a claim of infringement. The observance of all legal regulations and patents is the responsibility of the user.

SUNCHEMICAL, and ElvaJet are either registered trademarks or trademarks of Sun Chemical Corporation in the United States and/or other countries. DIC is a trademark of DIC Corporation, registered in the United States and/or other countries. Copyright © 2020 Sun Chemical Corporation. All rights reserved.

Sun Chemical Ltd.
Norton Hill
Midsomer Norton
BA3 4RT
United Kingdom
Tel: +44 (0)1761 414471

**Sun Chemical Advanced
Materials SA**
ZI Riond Bosson 8
Morges
CH-1110, Switzerland
Tel: +41 21 811 2300

Sun Chemical US
35 Waterview Boulevard
Parsippany
NJ 07934
Tel: +1 0973 404 6600